



# OxyVinyls® 190F

## General Description

Type:	Polyvinyl Chloride Homopolymer
Polymerization Process:	Suspension
Appearance:	White, free flowing powder

## Features and Uses:

Extrusions, foams, clear film and sheet	Calendering
Injection molding, Pipe fittings	Alloying
Solution top coats	Flooring

## Resin Properties

	Specification Range	Test Method
Inherent Viscosity (dl/g)	0.710 – 0.750	OxyVinyls 1386
Relative Viscosity	1.86 – 1.92	Correlation
K Value	57 – 59	Correlation
Volatiles (%)	0.30 Max.	OxyVinyls 1242
Malvern Particle Size		
% Retained on 40 mesh	0.5 Max.	OxyVinyls 1505
% Retained on 60 mesh	4.0 Max.	OxyVinyls 1502
% Retained on 200 mesh	25.0 Max.	
% Retained on Pan	6.0 Max.	
Contamination (#/100gm)	15 Max.	OxyVinyls 1504
Residual Monomer (ppm)	1.0 Max.	OxyVinyls 1005
Apparent Bulk Density (g/cc)	0.515 – 0.595	OxyVinyls 1501
Flow Time (s)	14 Max.	OxyVinyls 1501
Gels (BEST Test)	10 Max.	OxyVinyls 1249
Color (CIE Lab b* Value)	0.50 – 1.40	OxyVinyls 1500

## Oxy Vinyls, LP

5005 LBJ Freeway  
 Dallas, Texas 75244  
 877-699-8465

**Important:** The information presented herein, while not guaranteed, was prepared by technical personnel and is true and accurate to the best of our knowledge. No warranty or guarantee, express or implied, is made regarding performance, stability or otherwise. This information is not intended to be all-inclusive as the manner and conditions of use, handling, storage and other factors may involve other or additional safety or performance considerations. While our technical personnel will be happy to respond to questions regarding safe handling and use procedures, safe handling and use remains the responsibility of the customer. No suggestions for use are intended as, and nothing herein shall be construed as a recommendation to infringe any existing patents or to violate any Federal, State, or local laws.